

Fraunhofer

TESTED® DEVICE

DENSO WAVE Inc. SUS630-H900 (Cutting)

Report No. DE 1409-725

Statement of Qualification

Hydrogen Peroxide Absorption/Desorption





Statement of Qualification

Customer DENSO WAVE Inc.

1, Yoshiike, Kusaki, Agui-cho, Chita-gun

470-2297 Aichi

Japan

Component tested

Category: Materials

Subcategory: Metals

Product name: SUS630-H900 (Cutting) (manufacturing date: 7/2014)

Hydrogen peroxide absorption / desorption

Methodics:

Air-conditioned laboratory environment:

Test procedure parameters:

- Material exposure to vaporized hydrogen peroxide for a defined duration using an emission test cell
- Aeration (with ambient air) of the test setup with continuous monitoring of the decreasing hydrogen peroxide concentration
- Calculation of the k-value as time needed to reach 1/10 of the maximum hydrogen peroxide concentration measured at start of the aeration

Temperature:	22°C±0,5°C
Chamber diameter:	65 mm
Chamber height:	5 mm
Exposed surface area:	33 cm ²
H2O2 vapor concentration:	50 ± 20 ppm (V)
Purge flow rate:	150l/h
Measurement flow rate:	100l/h
Excess air flow rate:	50l/h

Test result/Classification

Ø k-value [min]	Standard deviation [min]	Classification
0.3	0.6	non-absorptive

The k-value (expressed in minutes) represents the required decay time to reduce the hydrogen peroxide vapor concentration measured at the beginning of the aeration phase to one tenth of the original concentration. The material classification is based on three separate measurements. The blank value of the test setup is subtracted from each measurement value. The average k-value is transferred to the following classification:

• <5 min:	non-absorptive
• 5-15 min:	fast
• 15-60 min:	average
• >60 min:	slow
Not determinable:	catalytic activity

The k-value can only be used to make a comparative material assessment. Provided the maximum hydrogen peroxide vapor concentration during material exposure is within the defined limit, it does not affect the calculated k-values.

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

For further information about the test environment and parameters, please refer to the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA

Department of Ultraclean Technology and Micromanufacturing

Nobelstrasse 12 70569 Stuttgart Germany Stuttgart, July 15, 2015

Place, date of first document issued

Place, current date

IA Molo Sommes

This document only applies to the named product in an unchanged state and is valid from the date of issue for a period of 5 years. The document can be verified under www.tested-device.com

