



Fraunhofer

**TESTED[®]
DEVICE**

Ziehl-Abegg SE
PA6-GF30 blue

Report No. ZI 1709-953

DUPLICATE

Statement of
Qualification

Outgassing Behavior
Ammoniac

Statement of Qualification

Customer
 Ziehl-Abegg SE
 Heinz-Ziehl-Strasse 1
 74653 Künzelsau
 Germany

Component tested

Category: Materials
 Subcategory: Plastics
 Product name: PA6-GF30 blue
 (manufacturing date: 7/20/2017; color: blue; serial number: 00412286)

Emission chamber measurements with gas impaction in combination with ion chromatography (IC)

Standards/Guidelines: ISO 14644-8; ISO/DIS 14644-15; VDI 2083 Part 17; VDI 2452 Part 1 (impinger); ISO 14911 (cations)
 The norms stated generally refer to the version valid at the time of the tests.

Testing equipment:

- Measuring station:.....Metrohm Professional IC 850
- Sampling chamber:.....Markes International µCTE

Sample storage:

- Age of sample:63 days
- Pre-conditioning
 - Cleanroom Air Cleanliness Class (according to ISO 14644-1):..... ISO 1
 - Airflow velocity:0.45 m/s
 - Airflow type:..... vertical laminar flow
 - Temperature:22 °C ± 0.5 °C
 - Relative humidity: 45 % ± 5 %
 - Purified air: VOC-filtered

Test procedure parameters: Outgassing test temperatures: 23 °C and 90 °C

Test result / Classification

The outgassing behavior of PA6-GF30 blue the stated temperatures was investigated according to VDI 2083 Part 17. Based on the outgassing rates determined for the specific surfaces, the following material classification was made for the corresponding Contaminant Category:

| Contaminat Category (x) | SER _a ¹⁾ 23 °C [g/m ² s] | SER _a ¹⁾ 90 °C [g/m ² s] | ISO-ACC _m Class (x) based on 23 °C |
|-----------------------------|---|---|---|
| Ammoniac (NH ₃) | < 6.9 x 10 ⁻¹⁰ | 5.6 x 10 ⁻⁷ | < -9.2 |

¹⁾ SER_a: Area-specific emission rate

The detection limit at the time of the test was ISO-ACC_m Class = -9.2 (NH₃). The ISO-ACC_m Class (x) was assigned for the named contaminat categories at the test temperature of 23 °C (room temperature).

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA

ZI 1709-953
 Report No. first document

Stuttgart, December 15, 2017
 Place, date of first document issued

Department of Ultraclean Technology and Micromanufacturing

--
 Report No. current document

--
 Place, current date

Nobelstrasse 12
 70569 Stuttgart
 Germany

on behalf of 
 Dr.-Ing. Frank Bürger, Project Manager Fraunhofer IPA