



Fraunhofer

**TESTED[®]
DEVICE**

Roche Diagnostics GmbH
MA Terrazzo LW standard
Report No. RO 1702-883

DUPLICATE

Statement of
Qualification

Chemical Resistance

Statement of Qualification

Customer
 Roche Diagnostics GmbH
 Sandhofer Strasse 116
 68305 Mannheim
 Germany

Component tested

Category: Materials
 Subcategory: Plastics
 Product name: Roche Mannheim Terrazzo LW standard
 (surface: smooth)

Chemical resistance test

Standards/Guidelines: VDI 2083 Part 17; ISO 2812-1; ISO 4626-1
 The norms stated generally refer to the version valid at the time of the tests.

Testing equipment:

- Microscope
- Camera

Test environment parameters: Temperature:.....22 °C ± 0.5 °C

Test procedure parameters:

- Immersion method
- Chemicals: Purified water 100 %
 Ethanol 100 %
- Incubation time:..... 1 h, 3 h, 6 h, 24 h

Test result / Classification

The chemical resistance of Roche Mannheim Terrazzo LW standard was classified according to ISO 4628-1 and VDI 2083 Part 17 with the following result:

Chemical resistance	1 h	3 h	6 h	24 h
Ethanol 100 %	0	1	1	2
Purified water 100 %	0	0	0	0

The classification is based on a worst-case consideration. In the process, damage was assessed according to the classification system used in ISO 4628-1 and VDI 2083 Part 17:

0 = excellent 3 = weak
 1 = very good 4 = very weak
 2 = good 5 = none

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA

RO 1702-883
 Report No. first document

Stuttgart, March 21, 2018
 Place, date of first document issued

Department of Ultraclean Technology and Micromanufacturing

--
 Report No. current document

--
 Place, current date

Nobelstrasse 12
 70569 Stuttgart
 Germany

on behalf of 
 Dr.-Ing. Frank Bürger, Project Manager Fraunhofer IPA