



Fraunhofer

**TESTED[®]
DEVICE**

Coopers Fire Ltd
Stainless Steel Structure 1.4044
Report No. CO 1804-1029

DUPLICATE

Statement of
Qualification

Chemical Resistance

Statement of Qualification

Customer

Coopers Fire Ltd
Edward House, Penner Road, Havant
Hampshire, PO9 1QZ
United Kingdom

Component tested

Category: Materials
Subcategory: Metals
Product name: Stainless Steel Structure 1.4044
(manufacturing date: 12/2017)

Chemical resistance test

Standards/Guidelines: VDI 2083 Part 17; ISO 4628-1; ISO 2812-1
The norms stated generally refer to the version valid at the time of the tests.

Testing equipment:

- Microscope
- Camera

Test environment parameters: Temperature: 22°C ± 0.5°C

Test procedure parameters:

- Immersion method
- Chemicals: Formalin 37 %
..... Ammoniac 25 %
..... Hydrogen peroxide 30 %
..... Sulfuric acid 5 %
..... Phosphoric acid 30 %
..... Peracetic acid 15 %
..... Hydrochloric acid 5 %
..... Isopropanol 100 %
..... Sodium hydroxide 5 %
..... Sodium hypochlorite 5 %
- Incubation time: 1 h, 3 h, 6 h, 24 h

Test result / Classification

The chemical resistance of the Stainless Steel Structure 1.4044 was classified according to ISO 4628-1 and VDI 2083 Part 17 with the following result:

Chemical resistance	1 h	3 h	6 h	24 h
Formalin 37 %	0	0	0	0
Ammoniac 25 %	0	0	0	0
Hydrogen peroxide 30 %	0	0	0	0
Sulfuric acid 5 %	0	0	0	0
Phosphoric acid 30 %	0	0	0	0
Peracetic acid 15 %	0	0	0	0
Hydrochloric acid 5 %	3	3	3	3
Isopropanol 100 %	0	0	0	0
Sodium hydroxide 5 %	0	0	0	0
Sodium hypochlorite 5 %	0	0	0	0

The classification is based on a worst-case consideration. In the process, damage was assessed according to the classification system used in ISO 4628-1 and VDI 2083 Part 17:

0 = excellent 3 = weak
1 = very good 4 = very weak
2 = good 5 = none

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA

CO 1804-1029
Report No. first document

Stuttgart, June 19, 2018
Place, date of first document issued

Department of Ultraclean Technology and Micromanufacturing

--
Report No. current document

--
Place, current date

Nobelstrasse 12
70569 Stuttgart
Germany

on behalf of 
Dr.-Ing. Frank Bürger, Project Manager Fraunhofer IPA