



Fraunhofer

TESTED[®]
DEVICE

AKA LIGHTING GmbH
PE powdercoating PO-658-9010-001
Report No. AK 2507-1654

DUPLICATE

Statement of
Qualification

Single product
Hydrogen Peroxide
Absorption/Desorption

Customer	AKA LIGHTING GmbH Siemensstrasse 6 71101 Schönaich Germany
Tested product	
Category:	Cleanroom Facilities
Subcategory:	Lighting Systems
Product name:	Polyester powdercoating PO-658-9010-001 (manufacturing date: 4/2025; color: RAL9010; article number: PO-658-9010-001)

Hydrogen peroxide absorption / desorption	
Standards/guidelines:	VDI 2083 Part 20 The norms stated generally refer to the version valid at the time of the tests.
Air-conditioned laboratory environment:	Temperature: 22 °C ± 0.5 °C
Test procedure parameters:	- Emission test cell volume: 16.5 cm³ - Exposed surface area: 33 cm² - H₂O₂ vapor concentration: 50 ± 20 ppm(V) - Exposure duration: 60 min - Air exchange rate during aeration:..... 50 min⁻¹ - Test cell: 23 °C ± 2 °C

Test result / Classification	The hydrogen peroxide absorption/desorption of Polyester powdercoating PO-658-9010-001 was investigated with the stated test parameters. Using the procedure laid down in VDI 2083 Part 20, the following test result was obtained:
------------------------------	---

Ø k-value [min]	Standard deviation [min]	Classification
2.36	0.43	non-absorptive

The k-value represents the required decay time to reduce the hydrogen peroxide vapor concentration measured at the beginning of the aeration phase to one tenth of the original concentration. The material classification is based on three separate measurements. The blank value of the test setup is subtracted from each measurement value. The medium k-value is transferred to the following classification:

- ≤ 5 min: non-absorptive
- > 5-≤ 15 min: fast
- > 15-≤ 60 min: medium
- > 60 min: slow
- Not determinable: catalytic activity

The k-value can only be used to make a comparative material assessment. Provided the maximum hydrogen peroxide vapor concentration during material exposure is within the defined limit, it does not affect the calculated

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA	AK 2507-1654 Report No. first document	Stuttgart, February 6, 2026 Place, date of first document issued
Business unit Testing and Certification	-- Report No. current document	-- Place, current date
Nobelstrasse 12 70569 Stuttgart Germany	on behalf of Dr.-Ing. Frank Bürger, head of business unit Testing and Certification	